



revoseal Europe GmbH
 Industriestraße 1
 50259 Pulheim Germany

T: +49 (0) 2238 47 999-0
 F: +49 (0) 2238 47 999-20
 info@revoseal.com

Köln HRB 85682
 USt.-Id.-Nr. DE815586009

Geschäftsführung
 Kerstin Holle
 Dr. Ulrich Horsmann

JG / JP Media Reference List

Media	Pressure [bar]	Temperature [°C]
Butadien Gas		
Oxygen, Ammonia		
Oxygen, Process Gas		> 538
Oxygen, Process Gas		> 538
Ammonia, Melamin, other chemicals		
Hydrocarbons, Corrosive Comp. , Gases , Ammonia		550
Hydrogen, Hydrofluoric acid		400
Hydrogen chloride (HCL), Dichloroethane (DCE), Vinyl chloride (VC), Steam	40	700
R134a / R133a (coolant); Hydrogen chloride; Oxygen; Hydrogen fluoride	10	200 to 430
Steam	20 to 160	120 to 300
Vacuum distillation: Toluene diisocyanate (TDI), Hexamethylene diisocyanate (HDI), Isophorone diisocyanate (IPDI)	0,5	20 to 200
Polyester	vacuum	60 - 280
Phosgene (gas)	3	150
Phosgene (solution)	12	10 to 80
Acetic acid (gas)	1	700 to 750
C ₃ , C ₄ , gas/petrol	15 to 30	~ 240
Organic chemistry	0,002	180
Ethylene Oxide; Dimethyl Ether; Methyl Chloride; Propylene Oxide	-1 to 25	-20 to 100
Acetylene		> 550
Chloric Gas, Oxygen, hydrochloric acid (gas)	2,2	400
Caustic Soda (suspension)	25	285
Water	0 - 10	20 - 160
Aromatic amine	3	20 - 250
Syngas	320	90
Hydrogen, H ₂ /CO		

